

Ángulo Extruido - 304



Composición química y propiedades

C% Max	Mn% Max	P% Max	S% Max	Si% Max	Cr% Max	Ni% Max	N% Max
0.08	2.00	0.045	0.030	0.75	18.0 – 20.0	8.0 – 10.5	0.10

Espesores, medidas y pesos

Ancho	1/8" kg/m	3/16" kg/m	1/4" kg/m	3/8" kg/m
1" 1	1.40 2.05	1.95 3.00	2.50	3.55 5.33
1/2" 2"	2.75 4.20	4.00 6.00	3.90	7.10 11.36
3" 4"	5.60	8.00	5.25	14.85
			8.10	
			10.00	