

Barras redondas y cuadradas -304



Composición química y propiedades

C%	Mn%	P%	S%	Si%	Cr%	Ni%	N%	
Max	Max	Max	Max	Max	Max	Max	Max	
0.08	2.00	0.045	0.030	0.75	18.0 – 20.0	8.0 – 10.5	0.10	

Diámetros y pesos

DIAM. PULG	KG/MT
3/16"	0.15
1/4"	0.26
5/16"	0.40
3/8"	0.60
1/2"	1.05
5/8"	1.60
3/4"	2.25
1"	4.20
1 1/4"	6.50
1 1/2"	9.00
2"	16.00
2 1/2"	25.30
3"	36.00
4"	64.00