


Placa - 304



Placa – 304

Acabados A1 Rolado en caliente, recocido y desincrustado. Generalmente usado para aplicaciones industriales en donde la textura del acabado no es importante.

Composición química y propiedades

C%	Mn%	P%	S%	Si%	Cr%	Ni%	N%
Max	Max	Max	Max	Max			
0.08	2.0	0.045	0.030	0.75	18.0 – 20.0	8.0 – 10.5	0.10

Tabla de pesos

Grueso	mm	4 x 10 1219 x 3048	4 x 20 1219 x 6096	5 x 10 1524 x 3048	5 x 20 1524 x 6096
3/16"	4.76	143	286	179	358
1/4"	6.35	191	382	233	466
5/16"	7.94	233	466	291	582
3/8"	9.53	286	572	357	714
1/2"	12.70	381	762	479	958
5/8"	15.74	467	934	585	1170
3/4"	19.05	571	1142	717	1434
1"	25.40	762	1524	956	1912